

environment matters

Plastic FPP RP001

Technical Data Sheet

Are you
ready to make
the switch?

Plastic | FPP RP001

Material	<ul style="list-style-type: none"> Recycled Black PP Calcium carbonate 23% filled Injection/extrusion grade
General Information	<ul style="list-style-type: none"> Recycled black PP co-polymer 75% post-consumer recycled content
Attributes	<ul style="list-style-type: none"> Even and consistent appearance Good resistance to fatigue Tough and flexible
Packaging	<ul style="list-style-type: none"> 1 tonne bulk bags



Mechanical Properties

Mechanical Property	Test Method	Unit Measurement	Spec	
			Min	Max
Density	ISO 1183-1	g/cm ³	1.10	1.14
Melt Flow	ISO 1133 - 230°C, 2.16Kg	g/10min	7	12
Izod Notched Impact Strength	ISO 180 / A	KJ/m ²	≥6	-
Elongation At Break	ISO 527-2	%	≥20	-

Please note that the above information relates to average values obtained from various batches. Because of the nature of the source materials these values may vary. It is the customer's responsibility to optimise processing conditions and assure suitability for use in their own products. It is also advised that the material is pre dried prior to use.

Recycled plastic - a sustainable and cost effective alternative.

Contact us for further information on our range of plastic compounds:



T. 01775 670226
plastics@enva.com

Enva Plastics Limited

Tunnel Bank Road, Bourne, Lincs, PE10 0DJ